

## YTELSESERKLÆRINGEN

**Nr. 7056-05022025**

1.Varetypens unike identifikasjonskode: **Level Oppkant 7056**

2.Tilsiktet bruksområde: Benkeplater/ interiør.

3.Produsent: Lamintex. UL.WEGIERSKA 78 – Polen.

4.Autorisert representant: Fritzøe Engros AA, Postboks 2055, 3255 Larvik.

5.System eller systemer for vurdering og verifikasjon av byggevarers ytelser:

6a.Harmoniseret produktstandard: NS-EN 438-2 og 4 : 2016

Teknisk(e) kontrollorgan: NPD

6b. Europeisk bedømmelsesdokument: NPD

Europeisk teknisk bedømmelse: NPD

Teknisk bedømmelsesorgan: NPD

Tekniske kontrollorgan: NPD

7. Angitte ytelser:

| S. No.    | Properties                                          | Unit              | Specification & Test Method EN 438 2 & 4 :2016 | Specified values                             | Typical Results |
|-----------|-----------------------------------------------------|-------------------|------------------------------------------------|----------------------------------------------|-----------------|
|           | <b>Nominal Thickness &amp; Finish</b>               | mm                |                                                | 12.0 mm Suede Finish                         |                 |
| <b>1</b>  | Classification                                      |                   | EN 438-4- 4                                    | <b>Compact general purpose standard, CGS</b> |                 |
| <b>2</b>  | Thickness                                           | mm                | EN 438-2 – 5                                   | 12.0 ± 0.60                                  | complies        |
| <b>3</b>  | Length & width                                      | mm                | EN 438-2 – 6                                   | +10mm/ -Nil                                  | complies        |
| <b>4</b>  | Flatness (deviation)                                | mm/M              | EN 438-2 – 9                                   | 3.0 (max.)                                   | complies        |
| <b>5</b>  | Resistance to Surface Wear                          | Rev.              | EN 438-2 -10                                   | 350 (min.)                                   | complies        |
| <b>6</b>  | Resistance to Dry Heat (160° C)                     | Rating            | EN 438-2 -16                                   | Not worse than 4                             | 5               |
| <b>7</b>  | Resistance to water vapor                           | Rating            | EN 438-2 -14                                   | Not worse than 4                             | 5               |
|           | Resistance to wet heat (100°C)                      | Rating            | EN 438-2 -18                                   | Not worse than 4                             | 5               |
| <b>8</b>  | Resistance to Immersion in Boiling Water (2 hours)  |                   | EN 438-2 -12                                   |                                              |                 |
|           | Mass Increase                                       | %                 |                                                | 2.0 (max.)                                   | 0.56            |
|           | Thickness Increase                                  |                   |                                                | 2.0 (max.)                                   | 0.75            |
|           | Appearance                                          | Rating            |                                                | Not worse than 4                             | 5               |
| <b>9</b>  | Dimensional Stability at Elevated Temperature       |                   | EN 438-2 -17                                   |                                              |                 |
|           | Longitudinal Direction                              | %                 |                                                | 0.30(max.)                                   | 0.16            |
|           | Transverse Direction                                | %                 |                                                | 0.60(max)                                    | 0.25            |
| <b>10</b> | Resistance to Impact by Large Diameter Ball         |                   | EN 438-2 -21                                   |                                              |                 |
|           | Drop Height                                         | mm                |                                                | 1800                                         | 1900            |
|           | Diameter of Indentation                             | mm                |                                                | 10 (max)                                     | 8               |
| <b>11</b> | Resistance to Scratching                            | N                 | EN 438-2 -25                                   | 3.0 (min.)                                   | Complies        |
| <b>12</b> | Resistance to staining                              | Rating            | EN 438-2 -26                                   |                                              |                 |
|           | Group 1 & 2                                         |                   |                                                | 5                                            | 5               |
|           | Group 3                                             |                   |                                                | 4                                            | ≥ 4             |
| <b>13</b> | Light fastness (Xenon Arc Lamp)-Grey Scale Contrast | Rating            | EN 438-2 -27                                   | 4 to 5                                       | Complies        |
| <b>14</b> | Resistance to Crazeing                              | Rating            | EN 438-2 -24                                   | Not worse than 4                             | 5               |
| <b>15</b> | Flexural Modulus                                    | Mpa               | EN ISO 178:2003                                | 9000(min)                                    | Complies        |
| <b>16</b> | Flexural Strength                                   | Mpa               |                                                | 80 (min.)                                    | Complies        |
| <b>17</b> | Density                                             | g/cm <sup>3</sup> | EN ISO 1183 -1:2004                            | 1.35                                         | 1.38            |

8. Bruk av hensiktsmessig teknisk dokumentasjon og/eller spesifikk teknisk dokumentasjon:

Ytelser for denne byggevaren, som er anført ovenfor, er i overensstemmelse med de angitte ytelsene. Denne ytelseserklæringen er utarbeidet i overensstemmelse med forordning (EU) nr. 305/2011 under eneansvar til produsenten, som er anført ovenfor.

Underskrevet for produsenten og på dennes vegne av:

Larvik,  
05.02.2025.

*Jarle Anholt*

Jarle Anholt