

Declaration of Performance

Number DOP.GAR.30.EN

1. Navn - ID kode på produktet

Efficiency Poplar / Performance Poplar / Performance Ewood
Poppel kryssfiner

2. Tiltent bruk:

- a) Bindingskvalitetsklasse 1: For innvendig bruk som en strukturell komponent i tørre forhold EN 636-1
- b) Bindingskvalitetsklasse 2: For bruk, se a) og for beskyttet utvendig bruk som en strukturell komponent under fuktige forhold EN 636-2
- c) Bindingskvalitetsklasse 3: For bruk, se a) og b) og også for utvendig bruk som konstruksjonsdel. Kun værbestandig hvis riktig overflatebehandlet og kantforseglet EN 636-3..

3. Navn og adresse på produsent:

Company name:

GRUPO GARNICA PLYWOOD, S.A.

Parque San Miguel, 10 bajos

Logroño (La Rioja) SPAIN

Manufacturing site:

GARNICA PLYWOOD FUENMAYOR, S.L.U.

Ctra. Navarrete, 20

26360 FUENMAYOR (La Rioja) SPAIN

GARNICA PLYWOOD VALENCIA DE DON JUAN,
S.L.

Ctra. Villafer, km. 2

24200 VALENCIA DE DON JUAN (León) SPAIN

GARNICA PLYWOOD BAÑOS DE RIO TOBIA,
S.A.U. (I)

Camino de Berceo, s/n

26320 BAÑOS DE RÍO TOBÍA (La Rioja) SPAIN

GARNICA PLYWOOD BAÑOS DE RIO TOBIA,
S.A.U. (II)

Ctra. De Lerma, km. 376

26320 BAÑOS DE RÍO TOBÍA (La Rioja) SPAIN

5. System for produksjonskontroll
AVCP system 2+

6. Kontrollorgan:

- AENOR (No. 0099)
- Sertifikat på følgende ytelser:

GARNICA PLYWOOD FUENMAYOR, S.L.U.	0099/CPR/A65/0050
GARNICA PLYWOOD VALENCIA DE DON JUAN, S.L.	0099/CPR/A65/0048
GARNICA PLYWOOD BAÑOS DE RIO TOBIA, S.A.U. (I)	0099/CPR/A65/0047
GARNICA PLYWOOD BAÑOS DE RIO TOBIA, S.A.U. (II)	0099/CPR/A65/0048

7. Declared Performance:

values			Performance			Technical specification
Thickness			6 – 10mm	11 – 20mm	21 – 50mm	
Nº of layers			3-5	5-11	11-25	
Resistant properties	Bending	$f_m \parallel$ (N/mm²)	20,7	16,5	15,5	EN 13986:2006+A1:2015
		$f_m \perp$ (N/mm²)	14,7	18,7	19,3	
	Compression	$f_c \parallel$ (N/mm²)	12,6	13,9	14,5	
		$f_c \perp$ (N/mm²)	18,4	14,6	17,5	
	Traction	$f_t \parallel$ (N/mm²)	5,1	5,6	5,9	
		$f_t \perp$ (N/mm²)	7,5	5,9	7,1	
	Panel shear	f_v (N/mm²)	4,1	4,1	4,1	
	Planar shear	f_r (N/mm²)	0,7	0,7	0,7	
Modulus of Elasticity properties	Bending	$E_m \parallel$ (N/mm²)	3328	3061	2952	
		$E_m \perp$ (N/mm²)	2346	2988	3596	
	Compression	$E_c \parallel$ (N/mm²)	2600	2852	2983	
		$E_c \perp$ (N/mm²)	3788	3000	3598	
	Traction	$E_t \parallel$ (N/mm²)	2600	2852	2983	
		$E_t \perp$ (N/mm²)	3788	3000	3598	
	Panel shear	G_v (N/mm²)	349	349	349	
	Planar shear	G_r (N/mm²)	16	16	16	
Bonding quality (for intended uses)			Class 1			
			Class 2			
			Class 3			
Formaldehyde release			E1 (≤3,5 mg/h·m²)			
Reaction to fire (according to table 8 EN13986)			≥9mm D s2,d0 / D FL, S1 <9mm NPD			
Pentachlorophenol content			< 5 ppm			
Water vapour permeability (according to table 9 EN 13986)			Wet: 60 μ Dry: 175 μ			
Sound absorption (according to table 10 EN 13986)			Frequency range: 250 Hz to 500 Hz: 0.10 Frequency range: 1000 Hz to 2000 Hz: 0.30			
Thermal conductivity (λ) (according to table 11 EN 13986)			0.11 W/(m·K)			

Characteristic values obtained according to EN 326-2 procedures, from test results as per EN 310.

In compliance with EN 13986:2004+A1:2015

The performance of the product identified in point 1 is in conformity with the declared performance in point 7.

This declaration of performance is issued, according to Rule (UE) nº 305/2011, under the sole responsibility of the manufacturer identified in point 3.

Signed for and on behalf of the manufacturer:



The image shows a blue ink signature over a rectangular stamp. The stamp contains the company name 'garnica' in a stylized font, followed by 'GRUPO GARNICA PLYWOOD, S.A.' and the address 'Parque San Miguel, 10-110 - 26007 Logroño, La Rioja'.

Logroño, 17th May 2021

Bruno Martínez, COO (Chief Operating Officer)